



Annapapi S.r.l

Registro delle Imprese di Livorno n. 01263550491
R.E.A. n. 113794

capitale sociale euro 118.000 i.v.

Tel + 39 0586 425525-426464 fax+39 0586 425640

e-mail info@annapapi.it WEB www.annapapi.it

Via Nicolodi Nr.54 - 57121 Livorno



SCHEMA TECNICA LIKEGREEN FGI GR 50

Caratteristiche Fisiche / Meccaniche <i>Physical / mechanical properties Caracteristique physico/mechaniques Merkmal</i>		Norme <i>Test method Normes Normen</i>	Unità di misura <i>Unit of measurement Unité de mesure Masseinheit</i>	Valori <i>Values Valeur Sollwert</i>	
1	Peso <i>Weight</i>	ISO 9073.1	g/m ²	50 ± 10%	
2	Spessore <i>Thickness</i>	ISO 9073.2	mm	0.50 ± 0.10	
				Longitudinale (MD)	Trasversale (CD)
4	Carico a rottura <i>Tensile strength</i>	ISO 9073.3	daN	≥ 6.5	≥ 1.9
5	Allungamento a rottura <i>Extention at break</i>	ISO 9073.3	%	≤ 70	≤ 150
6	Carico a rottura (umido) <i>Tensile strength (wet)</i>	ISO 9073.3	daN	≥ 5.5	≥ 1.3
7	Allungamento a rottura (umido) <i>Extention at break (wet)</i>	ISO 9073.3	%	≤ 80	≤ 160
8	Capacità di assorbimento <i>Water absorptive capacity</i>	EDANA 10.2- 96/2	%	≥ 750	
9	Tempo di assorbimento <i>Water absorptive time</i>	EDANA 10.2- 96/1	Sec.	≤ 4	
10	Linting <i>Linting</i>	EDANA 300.0.84	g/m ²	≤ 3.0	